



Technical datasheet No.: **1067.10**
Product: VALMEX® print AIRTEX® FR
Article No.: 7513 5300

Type of coating and finish			
Type of coating	PUR		
Burning behaviour	BS 5867 Part 2 Type B, California T 19, D.M. 26.06.84 (UNI 9177): CL. 1, NFP 92507: M1, NFPA 701 Test 2, DIN 4102: B1		
for Burning behaviour	always check the validity of fire certificate		
Total weight	260 g/m ²	EN ISO 2286-2	
Tensile strength warp/weft	1200 / 1000 N/50 mm	EN ISO 1421/V1	
Tear strength warp/weft	130 / 80 N	DIN 53363	
Cold resistance	-30 °C	EN 1876-1	
High Temperature	+70 °C	PA 07.04 (intern)	
Crack resistance	no cracks	100000 x	DIN 53359 A
Base fabric			
Material	PES	DIN EN ISO 2076	
Weave	L 1/1		
Remarks	no phthalates, PVC-free		

These indicated technical data are based on average results. Due to production procedures deviations up to -5% can occur. All technical data are in accordance with the present standard of knowledge and give product information without legal binding. All data apply to new products. Applications suggested do not release the customer to test material for its intended application.